

C2 Guard Fusion

COVERAGE	VOC	REFLECTANCE	DRY TO TOUCH	DRY TO RECOAT	FULL CURE
Up to 300 sq ft/gal	<50 g/L	<5 @ 60°	15-30 Minutes	60 Minutes	Light use: 4-5 hrs; Full use: 24-36 hrs

Advanced protection with a beautiful soft sheen. C2 Fusion combines advanced acrylic and urethane technologies to create a durable, water-resistant finish with enhanced abrasion and UV resistance. Ideal for interior and exterior wood surfaces, it delivers long-lasting beauty while preserving the natural character of the wood.

SURFACE PREPARATION

Clean the surface to remove contaminants such as dirt, dust, oil, grease, wax, and rust. Remove any algae, mold, or mildew with appropriate cleaners, and rinse or pressure-wash away the cleaners.

Green lumber often has mill glaze that must be removed by sanding before application. Allow pressure-treated lumber to age for 3 - 6 months before application.

Apply a coat of C2 Guard before applying C2 Fusion. C2 Fusion is clear and provides additional protection over C2 Guard, which is available in a variety of stain colors.

APPLICATION INSTRUCTIONS

Stir thoroughly before and during application. Do not thin. Wait 60 minutes before applying the second coat.

On vertical surfaces, apply from bottom to top. Preferred application methods include a brush, pad, or pump sprayer. HVLP and airless spraying are also acceptable. Ensure the surface is generously coated when spraying.

For maximum performance, treat all six sides of the wood, paying particular attention to the end grain.

The surface may be used lightly 4 - 5 hours after application; allow 24 hours for full use. Drying time depends on surface porosity, temperature, and humidity.

Overspray: Clean overspray from unwanted areas with water while it is still wet.

TECHNICAL DATA

SKU	G4500	WEIGHT PER GALLON	8.5 +/- .2
SIZES AVAILABLE	1's (Quart), 5's, Gallon	VOLUME SOLIDS	19%
RESIN TYPE	Acrylic Resin		